

**PRODUCT INFORMATION**
**sawascreen<sup>®</sup> 8602**

<b>Type of Nonwoven</b>	Facemask	
<b>Recommendation for application</b>	FFP2 in acc. EN143	
<b>Fiber Composition</b>	Polypropylene	
<b>Property</b>	<b>Method</b>	<b>Average</b>
<b>Basis Weight</b>	NWSP 130.1	70 g/m <sup>2</sup>
<b>Thickness (0.05 N/cm<sup>2</sup>)</b>	NWSP 120.6	0,68 mm
<b>Air permeability (200 Pa)</b>	NWSP 70.1	200 l/m <sup>2</sup> /s
<b>Initial Pressure Drop (0.05 m/s) (95 l/min)</b>	NWSP 70.1	80 Pa
<b>Penetration (0.3 µm)</b>	DIN EN 779	2 %
<b>Initial efficiency DEHS (0.3 µm)</b>	DIN EN 779	98 %

This information is provided in good faith but Sandler cannot guarantee its accuracy or completeness. The end user is advised to evaluate the product and use it only in compliance with all applicable laws and regulations. This is not a specification. Properties are given as typical values.

Thickness measured under relaxed conditions. May vary after packaging, storage and transport.

The above mentioned data refer to developmental product and may be changed without prior notice.

SA 202